

# Metro Industries, Inc.

## Typical Material Specifications for SCE43B

### Polymer: Neoprene/EPDM/SBR

Physical Properties	Test Method	Unit of Measure	Result
Compression Deflection 25%	ASTM D1056	Psi	9 - 13
		kPa	62 – 89.6
Density	ASTM D1056	Pcf	7 - 11
		g/cm <sup>3</sup>	.112 - .176
Compression Set (MAX)	ASTM D1056	%	30
Water Absorption (Typical)	ASTM D1056	%	10
Tensile Strength (Typical)	ASTM D412 (Die A)	Psi	100
		kPa	690
Elongation (Typical)	ASTM D624 (Die C)	%	125
Tear Strength (Typical)	ASTM D624 (Die C)	lb/in	15
		kN/m	2.6

Specification	Result
ASTM D1056-67	SCE43
ASTM D1056-78	RE43
ASTM D1056-07	2A3
ASTM D1056 Suffix	A1, C1, F1, M
ASTM D6576-07	Type II A, B, C Medium
MIL-R-6130C	II-A Medium
MIL-R-3133C MIL STD 670B	SCE11
UL48	Listed
UL50	Listed
UL50E	Listed
UL157	Listed
UL508	Listed

Flammability Specification	Result
UL94 HF1	Listed
FMVSS-302	Pass (.098" or Thicker)

Additional Specifications	
Service Temperature	-40 °F to 200 °F
High Intermittent Temp	250 °F
Thermal Conductivity	.38 Btu-in/hr-FT <sup>2</sup> -°F